

GET THIS **LOOK**



GET THIS LOOK

SKILL LEVEL:
BEGINNER



Equipment



- Vinyl Cutter

Garment



SanMar® — SanMar® Sport-Tek® PosiCharge® Tri-Blend Wicking Raglan Tee, ST400

Materials



- ELASTI PRINTS® Screen Printed Transfer from Transfer Express®

Accessories



- None

How-To Instructions



Temperature: 300°F degrees

Pressure: Medium

1. Visit the Transfer Express® website, <https://transferexpress.com/heat-applied-transfers/elasti-prints-screen-printed-transfers>
2. Upload artwork or find and customize a design in the Easy View Designer; for this design, an ELASTI PRINTS® Screen Printed Transfer was ordered.
3. Cut apart transfer elements.
4. Load garment onto heat press.
5. Preheat to remove moisture and wrinkles from garment.
6. Place transfer 3" to 4" down from collar.
7. Press for 15 seconds.
8. Peel cold.
9. Spin shirt on heat press to decorate the back side.
10. Preheat to remove moisture and wrinkles from garment.
11. Place transfer 3" to 4" down from collar.
12. Press for 15 seconds.
13. Peel cold.